

SOLID ELECTROLYTE

[71] Applicant: FUKOKU CO LTD;
POLYTEC DESIGN:KK

[72] Inventors: OTA KEN; KURAMOCHI
HIROSHI

[21] Application No.: JP08208062

[22] Filed: 19960807

[43] Published: 19980217

[No drawing]

[Go to Fulltext](#)

[57] Abstract:

PROBLEM TO BE SOLVED: To obtain a solid electrolyte which has a high ionic conductivity in the temp. range from room to low temps. and is excellent in formability into a thin film, flexibility, and mechanical properties by selecting a solid electrolyte comprising a continuous phase consisting of a first polymer and an org. electrolyte compatible therewith and a support phase consisting of a second noncross- linked polymer incompatible with the org. electrolyte. SOLUTION: This solid electrolyte comprises a continuous phase consisting of a first polymer made up of at least one member selected among polymn. units represented by formulas I (wherein R¹ is H or methyl), II (wherein R² is H or methyl; and (n) is 1-5), and III (wherein R³ is H or methyl; (m) is 1- 3; l is 1-5; and X is O or S) and an org. electrolyte compatible therewith and a support layer consisting of a second noncross-linked polymer incompatible with the org. electrolyte. Pref. the amt. of the first polymer is 40-95wt.% of the sum of the first and second polymers, and that of the second polymer is 60-5wt.%. The amt. of the org. electrolyte is pref. 1-50 times that of the first polymer.

[51] Int'l Class: C08L03320 C08L03304 H01B00106 H01M00618
H01M00802 H01M00810 H01M01040